

# POWDER - Lak

(PTY) LTD

## Technical Information

### Powder – Lak Series 1000 Powder Paints

- Basic Material** A thermo-curing acidic, oil free polyurethane resin system.
- Product Indication** Powder-Lak Series 1000 or electrostatic powder spray application (EPS).
- Applications** POWDER-LAK Series 1000 is a single coat application, offering protection against weathering and chalking, and is particularly suitable for the coating of aluminum, steel and galvanized steel for exterior use.  
Due to excellent resistance to UV attack, the product offers excellent color stability and resistance to yellowing, and is suitable as a high quality interior finish for lighting fixtures, louvers, radiators, boilers, glass bottles etc.  
This product range has been approved by the SABS, according to SANS 1578:2006, as **Architectural exterior durable powder coating paints.**
- Properties** POWDER-LAK Series 1000 has excellent mechanical properties, e.g. surface hardness, impact and shock resistances, deformability, very good adhesion, excellent stability when exposed to light and weather, and retains a glossy appearance for extended periods.  
The resistance to chemical attack and corrosion is remarkable (ref. salt spray test), as well as the resistance to yellowing, even after excessive stoving.  
The resistance to solvents is good. However, in view of the multitude of cleaning solutions used these days, we recommend checking whether the film dissolves by some cleaner, or whether other changes occur (such as loss of gloss or softening of the surf
- Application** POWDER-LAK Series 1000 may be applied using any electrostatic high voltage **Method** powder coating equipment, with a charge of 30 - 100Kv. The compressed air must be free of water and/or oil.  
The usual instructions of the equipment supplier must be followed concerning the preparation of recovered powder, the time/temperature baking cycle, cleaning of the spray booth and filter unit, and checking of the humidity. When powder coating is done with hand-held equipment, adequate **Personal Protective Equipment** must be worn.
- Curing Schedule** 200°C for 20 minutes (metal temperature)

## Technical Information

### Powder – Lak Series 1000 Powder Paints TGIC Free

<b>Powder Data</b>	<ol style="list-style-type: none"><li>1. Particle size: max. 125 <math>\mu</math>. The particle size is determined by an ALPINE Air Jet Sieve (DIN 53734).</li><li>2. Specific Gravity: 1,2-1,8 (depending on tint and type).</li><li>3. Coating thicknesses: 60-120 <math>\mu</math> (for cold workpieces); up to 350 <math>\mu</math> (for preheated workpieces)</li><li>4. Theoretical Coverage: 5-10 sq. m/kg. with 60 - 80 <math>\mu</math> depending on the type.</li></ol>
<b>Colors</b>	Many RAL and SABS colors, standard colors as per the color card. Special colors on request, subject to minimum quantities.
<b>Gloss</b> (GARDNER DIN 67530)	25 – 90% (Gloss, semi-matt and matt qualities, special textures)
<b>Curing loss</b>	0,4-0,6%
<b>Shelf life</b>	About 6 months if stored in a cool, dry environment, not in excess of 25°C. Prevent exposure to sun and heat radiation, as these will affect the flow characteristics and gel time. Shelf life can be extended to 12 months if optimal storage conditions are met.
<b>Packaging</b>	20kg non-returnable, box with polythene bag.
<b>Cleaning of jigs</b>	With commercially available solvents or hot alkaline baths.
<b>Repair coating</b>	With 2K repair coatings
<b>Advantages</b>	Single coat with thicknesses of 40 - 150 $\mu$ . User-friendly, as no solvents are required. Reduced fire hazard, good edge covering. Loss reduced to 3 - 5% due to recovery of material, clean working stations, no evaporation period, low porosity of coating, excellent insulation. If coating is done correctly, no pollution. No dripping or running during application.

# Technical Information

## Powder – Lak Series 1000 Powder Paints

### TECHNICAL DATA

<b>Surface</b>	Aluminum plate, (chromate conversion pretreatment)
<b>Coating thickness</b>	70 +/- 10 $\mu$ .
<b>Pendulum hardness</b> (DIN 53157)	180 - 200 secs.
<b>Cross Hatch</b> (DIN 53151)	Gt0
<b>ERICHSEN cupping</b> (DIN 53156)	5-9 mm (depending on formulation), 3-6 mm (semi-matt and texture finishes)
<b>BUCHHOLZ Hardness</b> (DIN 53153)	80-100
<b>Spindle-bend test</b> (DIN 53152)	Up to 5 mm for standard formulations 8-12 mm for semi-matt and texture finishes
<b>Impact test GARDNER</b>	> 8 Joules
<b>Abrasion test</b> (ERICHSEN abrasion with 400 double lift motions)	40 +/- 10 mg.
<b>Salt Spray test</b> ASTM B 177-61	240 - 1200 hours depending on type. Disbonding on Andreas cross: about 1 mm
<b>Temperature resistance</b>	Briefly: up to 180°C Long periods: up to 120°C * * No mechanical stress (slight yellowing of bright colors)
<b>Dew point environment</b> DIN 50017	500 hours with no disbonding (when suitably pretreated).
<b>Toxicological properties</b>	The LD-50 figures for the resins and hardeners used are available.
<b>NOTE:</b>	Test results apply to powders applied under controlled conditions. Variations may occur due to the surface, application, pre-treatment, curing, etc.

The data on this information sheet does not constitute a guarantee.